



Lyrics for song "My Way" removed for
copyright reasons.

3.320
Last Lecture
(May 10 2005)

Overview

Basic Techniques

DFT and Potentials

MD, MC

Often need to be combined in creative ways to get results

Issues: How to make impact ?

Methods: DFT++

DFT and Potentials
MD, MC
Coarse-graining

Knowledge:

Basic Science of your field

What to compute

Tools


**Materials
Problem**

People


Dissemination

 Publish, educate and code development.


Education:

 Computational Materials Science/Chemistry is still the step child in Educational Curricula

Theory of Properties: The Multi-Scale Materials View



Theory of Properties: A More Realistic View



Courtesy of NIH.

**Computations should not substitute
for lack of knowledge**

Example: Intergranular Embrittlement of Fe

Observation: **P embrittles high strength steel**
 B enhances intergranular cohesion

Can we study this with atomistic modeling ?

Rice-Wang theory

"Embritting tendency of solute depends on difference in segregation energy at grain boundary and free surface"

Calculate segregation energy for B and P at free surface and grain boundary

Intergranular Embrittlement of Fe

Rice-Wang theory

"Embritting tendency of solute depends on difference in segregation energy at grain boundary and free surface"

Diagram removed for copyright reasons.
Source: Wu, R., A. J. Freeman, and G. B. Olsen. *Science* 265 (1994): 376-380.

Calculate segregation energy for B and P at free surface and grain boundary

Intergranular Embrittlement of Fe

Graph and diagrams removed for copyright reasons.

**R. Wu, A. J. Freeman, G. B. Olson, *Science* 265,
(1994) 376-380 .**

**When you can not think through the
relation between macroscopic behavior and
“computable” properties on the atomic
scale**

Derive relation statistically -> data
mining techniques

What if we can not bridge the gap between microscopic and macroscopic with theory ?

Microscopic


Macroscopic

Use large amounts of data for which macroscopic property is known

Photo of hands counting money removed for copyright reasons.

Correlate ?


Properties



Electrons


Makes it possible to deal with properties for which one has no microscopic theory or approach

Learning Methods



e.g QSAR in chemistry (Quantitative Structure Activity Relationship)


Example, can one predict stable crystal structures in a binary alloy from knowledge of only the energy of a few compounds



Ag-Cd: Example

Image removed for copyright reasons.

Test : Crystal Structure Prediction



~4x speedup from Data Mining

Design: Bandgaps

Standard First Principles Methods (LDA/GGA) underestimate band gaps

Example: Silicon

Figure removed for copyright reasons.

Calculated: 0.55 eV

Experimental: 1.1 eV

Can be fixed

With empirical pseudo potentials (not generally available) band gaps can be corrected by fitting to well-known semi conductors

GaAs

Si

Figure removed for copyright reasons.

Then, can predict band gaps of mixtures and states of impurities

Figure removed for copyright reasons.

Figure removed for copyright reasons.

Can try to find composition and arrangement with “tuned” gap

Scan through millions
of AlAs/GaAs
superlattices to find
one with maximal band
gap

Figure removed for copyright reasons.

Thermoelectrics

Figure of merit

$$ZT = \frac{\sigma}{\kappa} S^2 T$$

Seebeck Coefficient



Want **low thermal conductivity**: Can be calculated, but tedious. Use qualitative guidelines:

Complex unit cells, “rattling” ions to cause scattering of phonons

e.g. skutterudites

Figure removed for copyright reasons.

Thermoelectrics

Want semiconductors with high s and high S

$$S = \frac{e\tau}{3\sigma T} \int d\varepsilon \left(-\frac{\partial f}{\partial \varepsilon} \right) N(\varepsilon) v^2(\varepsilon) (\varepsilon - \varepsilon_o)$$



Can be calculated from band structures

Figure removed for copyright reasons.

Prediction of high thermo-electric performance



Figure removed for copyright reasons.

from Fornari and Singh: *Applied Physics Letters*, Vol 74, 3666 (1999)

The future of modeling

What does more computing buy you ?

Doubling every two years

40 years -> 10^6 increase in performance

Figure removed for copyright reasons.

But, ... scaling

Molecular Dynamics with potentials

$O(N)$

DFT (LDA, GGA)

$O(N^3 \text{ or } N^2 \log(n))$

Hartree Fock

$O(N^4)$

Method	Today (atoms)	+40 years
MD (potentials)	10^8 atoms	10^{14} atoms
LDA (N^3)	1000	100,000
LDA(N)	1000	10^9
HF +CI(N^6)	10	100

Scaling for length

$$N = L^3$$

Conclusion

Computational modeling is very powerful, but

Be Smart

